

Effect of concentration of hydrofluoric acid and etching time on microtensile bond strength of Zirconia-reinforced lithium silicate ceramics

Morteza Rostami ^{1✉}, Faraneh Mokhtarpour ^{2✉}, Homayoon Alaghehmand ^{3*}

1. Dental Student, Student Research Committee, Babol University of Medical Sciences, Babol, Iran.

2. Assistant Professor, Oral Health Research Center, Health Research Institute, Babol University of Medical Sciences, Babol, Iran.

3. Professor, Dental Materials Research Center, Health Research Institute, Babol University of Medical Sciences, Babol, Iran.

Article Type

ABSTRACT

Research Paper

Introduction: Etching the internal surface of ceramic restorations with hydrofluoric (HF) acid and silane is a well-accepted technique to enhance the bond strength. The aim of this study was to assess the effect of concentration of hydrofluoric acid and etching time on microtensile bond strength (μ TBS) of zirconia-reinforced lithium silicate (ZLS) ceramics in 2021.

Materials & Methods: This in vitro study was conducted on 8 Celtra-Duo ceramic blocks size 14 measuring 12×14×18 mm. Each ceramic block was divided into three equal pieces by a cutting machine to obtain a total of 24 specimens. The specimens were randomly divided into 6 groups for etching with 5% and 10% HF acid for 30, 60, and 120 seconds. Silane (Clearfil porcelain activator) and bonding agent (Clearfil SE Bond) were applied to the etched specimens. Panavia F2 resin cement was applied on the surfaces and light-cured. The μ TBS of resin cement to porcelain was measured by a universal testing machine. The mode of failure was determined under a stereomicroscope at x40 magnification. Data were analyzed by one- and two-way ANOVA ($P < 0.05$).

Results: The mean μ TBS of Celtra-Duo ceramics subjected to etching for 30, 60, and 120 seconds was not significantly different in the use of 5% and 10% HF acid concentrations ($P > 0.05$). Two-way ANOVA showed that the effects of HF acid concentration and etching time, and their interaction effect were not significant on μ TBS of CAD/CAM Celtra-Duo ceramics ($P > 0.05$). The mode of failure was dominantly adhesive in both concentrations of 5% and 10% HF acid. No mixed failure occurred in both concentrations.

Conclusion: Considering the non-significant difference in μ TBS of ceramics subjected to different concentrations of HF acid for different times, the application of HF acid with lower concentration for a shorter period is recommended to prevent possible adverse effects on ceramic strength.

Keywords: Ceramics, Dentistry, Hydrofluoric Acid, Resin Cements

Received : 10 Mar 2022

Received: 24 May 2022

Accepted: 7 Jun 2022

Pub.online: 11 Jul 2022

Cite this article: Rostami M, Mokhtarpour F, Alaghehmand H. Effect of concentration of hydrofluoric acid and etching time on microtensile bond strength of Zirconia-reinforced lithium silicate ceramics. *Caspian J Dent Res* 2022; 11: 77-84.



© The Author(s).

Publisher: Babol University of Medical Sciences

*Corresponding Author: Homayoon Alaghehmand, Department of Restorative Dentistry, Babol University of Medical Sciences, Babol, Iran.

Tel: +98 11 32202035

E-mail: halaghehmand@mubabol.ac.ir

Introduction

Ceramic restorations are widely used due to their excellent durability, esthetics, and biocompatibility. Dental ceramics can better mimic the appearance of natural teeth compared with other dental materials.^[1] Silicate minerals such as quartz and silica are the main constituents of dental ceramics. Modern dental ceramics have a higher content of the crystalline phase which significantly improves their biomechanical properties.^[2] Ceramic restorations can be fabricated by the conventional laboratory technique or the computer-aided design computer-aided manufacturing (CAD/CAM) systems.^[3-7] The CAD/CAM technology decreases the fabrication time of high-strength ceramics.^[4, 5] Moreover, the blocks fabricated by the CAD/CAM technology are more homogenous, and have fewer defects.^[8, 9] Long-term success of ceramic restorations depends on the strength and durability of the resin cement bond to porcelain and dental substrates.

In 1983, Horn suggested etching the surface of porcelain veneers with hydrofluoric acid (HA).^[10] A two-dimensional assessment of the etched surface indicates that the porcelain surface is selectively dissolved, depending on the porcelain composition. Accordingly, a surface more prepared for bonding is created as such.^[9, 10] Etching of the internal ceramic surface with HA followed by silane application is a documented technique for enhancement of bond strength.^[11]

Researchers have long been in search of novel restorative materials with favorable mechanical and esthetic properties. This search led to the introduction of zirconia-reinforced lithium silicate (ZLS) ceramics, which can be used for the fabrication of restorations with CAD/CAM technology.^[12] Two types of CAD/CAM ZLS ceramics are currently available in the market namely Vita Suprinity (Vita Zahnfabrik, Bad Säckingen, Germany) and Celtra-Due (Dentsply Sirona, DeguDent, GmbH, Hanau-Wolfgang, Germany). Celta-Duo ceramics have 10% zirconia in their structure, resulting in four times smaller lithium silicate crystals. These ceramics can provide a flexural strength as high as 210 MPa if polished manually, and 370 MPa if glazed in a furnace.^[13] Evidence shows that HF acid etching has the greatest efficacy for enhancement of the bond strength of porcelain with a glass matrix to resin cement.^[11] The kinetics of the reaction between HF acid and ceramic is influenced by the etching time and concentration of HF acid.^[10]

Since the introduction of HF acid for ceramic surface treatment prior to resin bonding, different etching times have been proposed. Also, ZLS is acid sensitive^[14], and it is important to clarify the ideal acid concentration and etching times for this ceramic type.^[12] However, no consensus has been reached on an ideal etching time with HF acid for the treatment of glass-ceramic restorations. Nonetheless, the manufacturer recommends 30 seconds of etching. Also, due to the novelty of these ceramics, it is important to find the shortest etching time that yields maximum bond strength and has no adverse effect on ceramics.^[15] Thus, this study aimed to assess the effect of three different etching times with two different concentrations of HF acid on microtensile bond strength (μ TBS) of CAD/CAM Celtra-Duo ceramics to resin cement. The null hypothesis was that increasing the etching time and concentration of HF acid would not increase the μ TBS of CAD/CAM Celtra-Due ceramics to resin cement.

Materials & Methods

This study was approved by the Ethics Committee of Babol University of Medical Sciences (ethical number: IR.MUBABOL.REC.1399.440). This in vitro experimental study was conducted at the Dental Materials Research

Center of School of Dentistry, Babol University of Medical Sciences in 2020-2021 on CAD/CAM Celtra Duo ceramic blocks.

•Specimen preparation: A total of 8 CAD/CAM Celtra-Duo ceramic blocks (#14) were selected. The sample size was calculated based on a previous study and the below formula.^[16]

$$n = \frac{\left(Z_{1-\frac{\alpha}{2}} + Z_{1-\beta} \right)^2 (S_1^2 + S_2^2)}{(d)^2} = 20, \alpha = 0.05, \beta = 0.20, S_1 = 4, S_2 = 2, d = 2.8$$

A total of 8 Celtra-Duo (Dentsply Sirona, DeguDent, GmbH, Hanau-Wolfgang, Germany) (#14) measuring 12×14×18 mm were used in this study. Each ceramic block was sectioned into three equal specimens by a cutting machine (Delta Precision Sectioning Machine, Mashhad, Iran). A total of 24 specimens were obtained as such (n=4 in each group). The surface of ceramic blocks was finished with a blue long fissure bur (D & Z) for standardization.^[17] Next, 5% and 10% concentrations of HF acid were manually prepared. To prepare 5% HF acid, 1 unit of 40% HF acid (Merck, Darmstadt, Germany) was mixed with 7 units of deionized distilled water. To prepare a 10% concentration of HF acid, 1 unit of 40% HF acid was mixed with 3 units of deionized distilled water. The ceramic specimens were randomly divided into two groups for use of 5% and 10% HF acid. Each group was then randomly divided into three subgroups for etching for 30, 60, and 120 seconds (a total of 6 subgroups). Each ceramic group then underwent etching with either 5% or 10% HF acid for 30, 60, or 120 seconds.

After etching, the ceramic specimens were rinsed with air and water spray for 30 seconds and placed in an ultrasonic bath (BioSonic UC50D, Coltene, Whaledent, USA) for 5 minutes to eliminate the residual salts. To eliminate the excess moisture, the specimens were immersed in 99% alcohol and dried with air spray. Table 1 presents the characteristics of the materials used in this study.

•Bonding procedure: One layer of silane (Clearfil Porcelain Bond Activator; Kuraray Medical Inc., Osaka, Japan) was applied to the etched ceramic specimens, dried, and thinned with air spray such that no additional liquid remained on the surface. This was done to create a single layer of porcelain primer for a stronger bond to the bonding agent. Next, one layer of bonding agent (Clearfil SE Bond; Kuraray Medical Inc., Osaka, Japan) was applied to the specimen surface.^[17] Panavia F2 cement (Kuraray Medical Inc., Osaka, Japan) was then applied on the prepared ceramic surfaces according to the manufacturer's instructions such that equal amounts of pastes A and B were mixed. The minimum mixing time was 20 seconds. The mixture with paste-like consistency was directly applied into a transparent mold with 6 mm diameter and 2 mm height, and the mold was placed on the silanized ceramic. Afterward, the cement surface was cured by a LED curing unit (Valo Corded, Ultradent, South Jordan, UT, USA) for 20 seconds with a light intensity of 1000 mW/cm².

Preparation process and microtensile bond strength test:

To prepare the micro-bars, ceramic-cement blocks were mounted in transparent epoxy resin in stainless steel molds (1×1 mm²). The mounted specimens were sectioned using a sectioning machine (Delta Precision Sectioning Machine, Mashhad, Iran) with a disc under running water. The sections had a slice interval of 1 mm and were made in two planes perpendicular to each other. Accordingly, micro-bars were obtained with a 1 mm² cross-sectional area and 4 mm height (2 mm of ceramic and 2 mm of resin cement). Five microbars were selected from each sample (each subgroup included 20 microbars). The microbars were subjected to a tensile force at a speed of 0.5 mm/minute in a universal testing machine (Koopaa, Sari, Iran) until failure. The tensile load in Newton (N) was

divided by the cross-sectional area in square millimeters (mm^2) measured by a digital caliper (Shinwa Rules Co., Niigata, Japan) to calculate the bond strength in megapascals (MPa). The μTBS of each specimen was calculated using the formula below: $\alpha=L/A$

Where L indicates load at failure, and A indicates the bonded surface area.

Table 1. Characteristics of the materials used in this study

| Material | Description | Manufacturer and Country | Composition and Batch Number |
|--|------------------------------------|------------------------------------|---|
| Panavia F2 | Dual-cure self-etch resin cement | Kuraray Medical Inc., Osaka, Japan | Paste A: hydrophobic aromatic and aliphatic dimethacrylate, hydrophilic aliphatic dimethacrylate, sodium aromatic sulfinate (TPBSS), N, Ndiethanol-p-toluidine, surface-treated (functionalized) sodium fluoride, 10%, silanated barium glass (61185); Paste B: MDP, hydrophobic aromatic and aliphatic dimethacrylate, hydrophilic aliphatic dimethacrylate, silanated silica, photoinitiator, dibenzoyl peroxide (61185) |
| Clearfil SE Bond | Light-cure self-etch adhesive | Kuraray Medical Inc., Osaka, Japan | Primer: MDP, HEMA, Hydrophilic dimethacrylate, N, N-Diethanol, p-toluidine, water(00109A) Bonding: MDP, Bis-GMA, HEMA hydrophobic dimethacrylate, dl-Camphorquinone, N, N-Diethanolp-toluidine, silanated silicate(00043A) |
| Clearfil Porcelain Bond Activator | one bottle of pre-activated silane | Kuraray Medical Inc., Osaka, Japan | Bisphenol A polyethoxydimethacrylate, 3-methacryloyloxypropyltrimethoxy Silane (00241A) |
| Celtra-Duo ceramic | Zirconia-reinforced glass-ceramic | Dentsply Sirona, Germany | 10% zirconia, 58% silica, lithium metasilicate, and phosphate crystals, SiO_2 , P_2O_5 , Al_2O_3 , LiO , ZnO , 10% ZrO_2 (16006396) |
| Hydrofluoric acid 40% | Liquid 40% hydrofluoric acid | Merck, Darmstadt, Germany | Chloride:1ppm, Hexafluorosilicate :50 ppm,phosphate:0.5 ppm,Sulphate:2 ppm, Arsenic & Antimony:0.03 ppm, Silver:0.020 ppm,Aluminium:0.050 ppm, Barium:0.050 ppm, Beryllium:0.020 ppm, Bismuth:0.020 ppm, Calcium:0.200 ppm (B0710538231) |

Assessment of the mode of failure: The mode of failure of specimens was determined under a stereomicroscope at x40 magnification. The failures were categorized into three categories of cohesive failure (fracture within the ceramic or cement), failure at the ceramic-cement interface (adhesive), and mixed failure (fracture of the ceramic, resin cement, and interface).

•Statistical analysis:Data were analyzed using SPSS version 26. One-way ANOVA and independent sample t-test were applied to compare different etching times. Two-way ANOVA was used to analyze the interaction effect of the variables. $P<0.05$ was considered statistically significant.

Results

The mean μ TBS of CAD/CAM Celtra-Duo ceramics subjected to 5% HF acid etching ($P=0.211$) and 10% HF acid etching ($P=0.724$) for 30, 60, and 120 seconds was the same with no significant difference (Table 2). The mean μ TBS of CAD/CAM Celtra-Duo ceramics etched for 30 ($P=0.107$), 60 ($P=0.707$), and 120 seconds ($P=0.773$) was not significantly different in the use of 5% and 10% HF acid. According to two-way ANOVA, the effects of HF acid concentration ($P=0.166$) and etching time ($P=0.433$), and the interaction effect of etching time and HF acid concentration ($P=0.153$) on μ TBS of CAD/CAM Celtra-Duo ceramics were not significant. The majority of failures in 5% and 10% HF acid groups were adhesive. Mixed failure was not seen in any of the 5% or 10% HF acid groups (Table 3).

Table 2. Mean and standard deviation of microtensile bond strength of CAD/CAM Celtra-Duo ceramics subjected to etching with different concentrations of HF acid for different times

| Etching time | 5% concentration | 10% concentration | P value** |
|--------------|--|--|-----------|
| | Mean and standard deviation of bond strength (MPa) | Mean and standard deviation of bond strength (MPa) | |
| 30 s (n=20) | 13.08±5.99 | 10.75±1.53 | 0.107 |
| 60 s (n=20) | 11.30±2.69 | 11.05±1.20 | 0.707 |
| 120 s (n=20) | 11.00±2.09 | 11.22±2.51 | 0.773 |
| P value* | 0.211 | 0.724 | - |

*ANOVA; **Independent sample t-test

Table 3. Frequency percentage of different failure modes in the study groups

| HF acid concentration | Etching time | Adhesive failure | Cohesive failure (fracture within the ceramic or cement) | Mixed failure |
|-----------------------|--------------|------------------|--|---------------|
| | 30 s | 14 | 6 | 0 |
| | 60 s | 13 | 7 | 0 |
| | 120 s | 15 | 5 | 0 |
| | 30 s | 11 | 9 | 0 |
| | 60 s | 12 | 8 | 0 |
| | 120 s | 10 | 10 | 0 |

Discussion

This study revealed that no significant difference in μ TBS of CAD/CAM Celtra-Duo ceramics etched with 5% and 10% HF acid with different etching times, and the null hypothesis of the study was accepted. Thus, the best etching time for CAD/CAM Celtra Duo ceramics is 30 seconds by using 5% HF acid.

The creation of sufficient porosity for a strong bond is influenced by the composition of ceramic.^[18] CAD/CAM Celtra-Duo ceramic has a high crystalline content (70 v%) in its glass matrix phase and contains 58% silica and

10% zirconia crystals along with lithium meta-silicate and phosphate crystals. Mokhtarpour et al. (2019) evaluated electron microscopic images and showed that increasing the etching time and concentration of HF acid can cause surface degradation in CAD/CAM ceramics and result in crack formation in them. Thus, a shorter etching time with a lower concentration of HF acid can provide optimal surface porosity for bonding.^[17] Similar to the present study, Mokhtarpour et al. (2017) in another study compared 5% and 10% concentrations of HF acid and 20, 60, and 120 second etching times and reported that the mean micro-shear bond strength (SBS) of e.max and Vita Mark II was not significantly different after using different concentrations of HF acid with different etching times. However, the maximum micro-SBS was recorded in e.max specimens etched with 5% HF acid for 60 seconds and Vita Mark II specimens etched with 10% HF acid for 20 seconds.^[16] They suggested etching with 5% HF acid for 20 seconds.

Fonzar et al. (2020)^[19] assessed the mean micro-SBS of Vita Suprinity ceramic and suggested etching with 4.9% HF acid for 20 seconds. They found a significant difference in bond strength between different concentrations of etchant, which was different from the present results. However, different etching times had no significant effect on the mean micro-SBS, which was in line with the present findings. Straface et al. (2019)^[20] found that 15 seconds of etching of Vita Suprinity ceramic with 5% HF acid yielded the maximum SBS. Longer etching times had no significant effect, and the efficacy of 30 seconds of etching was comparable to 60 seconds of etching. Yazarloo et al. (2019).^[18] evaluated the μ TBS of Suprinity ceramic and found that the best etching time was 120 seconds with 5% HF acid. Duration of etching and concentration of etchant significantly affected the μ TBS of Suprinity ceramic in their study, which was different from the present findings. Ramakrishnaiah et al. (2016) used 5% HF acid for 20, 40, 80, and 160 seconds for etching of IPS e.max, Vita Mark II, Suprinity, And Dentsply Celtra ceramics and found that increasing the etching time increased the depth and number of porosities, surface hardness, and surface wetting.^[21] Variations in the results of studies on this topic can be attributed to differences in ceramic types.

In the present study, 30 seconds of etching was selected as recommended by the manufacturer; the selection of 60 and 120 seconds of etching times was based on the results of Chen et al.^[22] To eliminate the possible confounding effect of other ingredients in the composition of commercially available porcelain etchants (in addition to HF acid), these concentrations were manually prepared in this study.

In this study, the majority of failures were adhesive. In general, cohesive failure had a higher frequency in 10% concentration of acid comparable to the frequency of adhesive failure. This finding indicates that the tensile strength of adhesive was almost similar to the cohesive strength of ceramic and cement. Adhesive failure indicates that the strength of the adhesive is stronger than that of the adherend, while cohesive failure indicates the lower strength of the adherend than the adhesive.^[16]

Several factors can affect the bond strength such as the cutting process of specimens, heterogeneity of the substrate, variations in material properties, technical sensitivity of the cement, and expertise of the operator, resulting in differences in the reported bond strength values.^[23]

This study had some limitations. The sectioning of ceramic blocks was difficult and time-consuming, and the materials were costly. Considering the different properties of ceramics, it is suggested to perform other tests on them. Also, the flexural strength of ceramics should be measured following the application of different concentrations of etchants with different application times.

Conclusion

Thus, it appears that the best etching time for CAD/CAM Celtra-Due ceramics with 5% HF acid would be 30 seconds.

Acknowledgments

The authors would like to thank the Dental Materials Research Center and Research Council of Babol University of Medical Sciences.

Funding

This manuscript was derived from a research project (Grant No: 724133368) which was supported and funded by Babol University of Medical Sciences.

Conflicts of Interest

There is no conflict of interests to declare

Authors' Contribution

Homayoon Alaghehmand developed the original idea and protocol. Morteza Rostami contributed to the development of the protocol, abstracted data and prepared the manuscript, and edited the article. Faraneh Mokhtarpour analyzed the data. Study supervision was conducted by Homayoon Alaghehmand.

References

- 1.Zogheib LV, Bona AD, Kimpara ET, McCabe JF. Effect of hydrofluoric acid etching duration on the roughness and flexural strength of a lithium disilicate-based glass ceramic. *Braz Dent J* 2011; 22: 45-50.
- 2.Ho GW, Matinlinna JP. Insights on Ceramics as Dental Materials. Part I: Ceramic Material Types in Dentistry. *Silicon* 2011; 3: 109-15.
- 3.Christensen R, Galan A, Mosher T. Clinical status of eleven CAD/CAM materials after one to twelve years of service. *State Art CAD/CAM Res* 2006; 20: 1-5.
- 4.Li RW, Chow TW, Matinlinna JP. Ceramic dental biomaterials and CAD/CAM technology: state of the art. *J Prosthodont Res* 2014; 58: 208-16.
- 5.Liu PR, Essig ME. Panorama of dental CAD/CAM restorative systems. *Compend Contin Educ Dent* 2008; 29: 482, 4, 6-8 passim.
- 6.Miyazaki T, Nakamura T, Matsumura H, Ban S, Kobayashi T. Current status of zirconia restoration. *J Prosthodont Res* 2013; 57: 236-61.
- 7.Takaba M, Tanaka S, Ishiura Y, Baba K. Implant-supported fixed dental prostheses with CAD/CAM-fabricated porcelain crown and zirconia-based framework. *J Prosthodont* 2013; 22: 402-7.
- 8.Hickel R, Manhart J. Longevity of restorations in posterior teeth and reasons for failure. *J Adhes Dent* 2001; 3: 45-64.
- 9.Manhart J, Chen H, Hamm G, Hickel R. Buonocore Memorial Lecture. Review of the clinical survival of direct and indirect restorations in posterior teeth of the permanent dentition. *Oper Dent* 2004; 29: 481-508.

10. Addison O, Marquis PM, Fleming GJ. The impact of hydrofluoric acid surface treatments on the performance of a porcelain laminate restorative material. *Dent Mater* 2007; 23: 461-8.
11. Ozcan M, Vallittu PK. Effect of surface conditioning methods on the bond strength of luting cement to ceramics. *Dent Mater* 2003; 19: 725-31.
12. Zarone F, Ruggiero G, Leone R, Breschi L, Leuci S, Sorrentino R. Zirconia-reinforced lithium silicate (ZLS) mechanical and biological properties: A literature review. *J Dent* 2021; 109: 103661.
13. Preis V, Behr M, Hahnel S, Rosentritt M. Influence of cementation on in vitro performance, marginal adaptation and fracture resistance of CAD/CAM-fabricated ZLS molar crowns. *Dent Mater* 2015; 31: 1363-9.
14. Altan B, Cinar S, Tuncelli B. Evaluation of shear bond strength of zirconia-based monolithic CAD-CAM materials to resin cement after different surface treatments. *Niger J Clin Pract* 2019; 22: 1475-82.
15. Xiaoping L, Dongfeng R, Silikas N. Effect of etching time and resin bond on the flexural strength of IPS e.max Press glass ceramic. *Dent Mater* 2014; 30: 330-6.
16. Mokhtarpour F, Alaghehmand H, Khafri S. Effect of hydrofluoric acid surface treatments on micro-shear bond strength of CAD/CAM ceramics. *Electron Physician* 2017; 9: 5487-93.
17. Mokhtarpour F, Alaghehmand H, Khafri S, Mahdian M. Effect of hydrofluoric acid concentration and etching time on the surface roughness of CAD/CAM ceramics. *Caspian J Dent Res* 2019; 8: 8-15.
18. Yazarloo F, Alaghehmand H, Mokhtarpour F. Effect of hydrofluoric acid concentration and etching time on microtensile bond strength of suprintity and enamic CAD/CAM ceramics to resin cement. *Caspian J Dent Res* 2019; 8: 16-23.
19. Fonzar RF, Goracci C, Carrabba M, Louca C, Ferrari M, Vichi A. Influence of acid concentration and etching time on composite cement adhesion to Lithium-silicate glass ceramics. *J Adhes Dent* 2020; 22: 175-82.
20. Straface A, Rupp L, Gintaute A, Fischer J, Zitzmann NU, Rohr N. HF etching of CAD/CAM materials: influence of HF concentration and etching time on shear bond strength. *Head Face Med* 2019; 15: 21-8.
21. Ramakrishnaiah R, Alkheraif AA, Divakar DD, Matinlinna JP, Vallittu PK. The Effect of Hydrofluoric Acid Etching Duration on the Surface Micromorphology, Roughness, and Wettability of Dental Ceramics. *Int J Mol Sci* 2016; 17: 822-30.
22. Chen JH, Matsumura H, Atsuta M. Effect of different etching periods on the bond strength of a composite resin to a machinable porcelain. *J Dent* 1998; 26: 53-8.
23. El Zohairy AA, Saber MH, Abdalla AI, Feilzer AJ. Efficacy of microtensile versus microshear bond testing for evaluation of bond strength of dental adhesive systems to enamel. *Dent Mater* 2010; 26: 848-54.