

The effect of bleaching on microhardness of silorane-based composite resins

Sedighe Sadat Hashemi Kamangar (DDS)¹✉, Kiana Kiakojoori (DDS)²,
Mansoore Mirzaii (DDS)³, Seyed Jalal Pourhashemi (DDS)⁴

1. Assistant Professor, Operative Dentistry Department, Dental School, Tehran University of Medical Sciences, International campus, Tehran-Iran.
2. General Dentist, Faculty of Dentistry, Babol University of Medical Sciences, Babol-Iran.
- 3 Assistant Professor, Operative Dentistry Department, Dental School, Tehran University of Medical Sciences, Tehran- Iran.
4. Associate Professor, Pediatric Dentistry Department, Dental School, Tehran University of Medical Sciences, International Campus, Tehran- Iran.

✉Corresponding Author: Sedighe Sadat Hashemi Kamangar, Dental School, Tehran University of Medical Sciences, International Campus, Tehran-Iran.

Email: smhk58950@gmail.com **Tel:** +982155851151

Received: 26 Apr 2014 Accepted: 23 Sept 2014

Abstract

Introduction: Bleaching treatments may negatively affect the surface quality of composite restorations existing in the mouth. This study sought to assess the effect of 16% and 35% carbamide peroxide on microhardness of silorane-based versus two methacrylate-based composite resins.

Methods: A total of 54 discs were fabricated from FiltekP90 (P90), FiltekZ350XT(Z350) Enamel and Filtek Z250(Z250) (n=18). Each group of composite specimens was randomly divided into 3 subgroups (n=6). The control subgroup was stored in distilled water for 2 weeks. Subgroup 2 specimens were bleached 4hours a day with 16% carbamide peroxide (Home bleaching) for 14 days. The 3rd subgroup specimens were subjected to 35% carbamide peroxide (Office bleaching) applied once for 40 minutes. Microhardness of specimens was measured before and after bleaching by using Vickers hardness testing machine. Data were analyzed by using Repeated Measures ANOVA.

Results: Baseline microhardness of P90 was lower than that of the other two composite resins ($p=0.001$). Bleaching decreased the microhardness of Z250 and Z350 compared to the control group ($p<0.001$). However, in P90, only the office bleaching material caused a reduction in microhardness ($p=0.009$). The effect of home and office bleaching on microhardness of P90 was different ($p=0.015$).

Conclusion: Bleaching treatments significantly decreased the microhardness of Z250 and Z350 composite resins but this reduction in P90 was not statistically significant after home bleaching.

Keywords: Hardness, Silorane composite resin, Tooth bleaching

Citation for article: Hashemi Kamangar SS, Kiakojoori K, Mirzaii M, Pourhashemi SJ. The effect of bleaching on microhardness of silorane-based composite resins. Caspian J Dent Res 2014; 3:46-53.

تأثیر بلیچینگ بر میکروهاردنس کامپوزیت بایس سایلوران

صدیقه السادات هاشمی کمانگر^{*}، کیانا کیاکجوری، منصور میزایی، سید جلال پورهاشمی

چکیده

مقدمه: درمانهای بلیچینگ ممکن است بر کیفیت سطح ترمیمهای کامپازیتی موجود در دهان اثر منفی داشته باشند. هدف این مطالعه تعیین اثر کارباماید پراکسید ۱۶٪ و ۳۵٪ بر ریزسختی کامپوزیتهای بایس سایلوران در مقایسه با دو کامپوزیت بایس متاکریلات می باشد.

مواد و روش ها: ۱۸ عدد دیسک کامپوزیتی با رنگ A3 از هر کدام از کامپازیت های Enamel, Filtek Z250 (Filtek P90, Filtek Z350XT) و در مجموع ۵۴ عدد با استفاده از مولد استنلس استیل ساخته شدند. هر یک از کامپوزیتها بصورت تصادفی به ۳ گروه مختلف تقسیم شدند. (n=6) یک گروه در آب مقطر به مدت ۲ هفته در دمای اتاق بعنوان نمونه های کنترل نگهداری شده و گروههای دیگر با کارباماید پراکساید ۱۶٪ (بلیچینگ در منزل)، ۴ ساعت در روز به مدت ۱۴ روز و کارباماید پراکساید ۳۵٪ (بلیچینگ در مطب) یکبار ۴۰ دقیقه، میزان ریزسختی نمونه ها قبل و بعد از بلیچینگ با استفاده از repeated measure ANOVA model Vickers hardness testing machine آنالیز شدند.

یافته ها: ریزسختی اولیه P90 به طور معناداری کمتر از دو کامپوزیت دیگر بود. در مورد Z250 و Z350 درمان بلیچینگ باعث کاهش معنادار میزان ریزسختی نسبت به گروه کنترل شد ($p<0.001$)، اما در مورد P90 فقط ماده بلیچینگ مطب باعث کاهش معنادار میکروهاردنس شد ($p=0.009$) اثر بلیچینگ خانگی و مطب بر P90 متفاوت بود (0.015).

نتیجه گیری: به دنبال درمان بلیچینگ ریزسختی کامپوزیتهای Z250 و Z350 به صورت معنی داری کاهش یافت ولی این کاهش به دنبال بلیچینگ در منزل در کامپوزیت P90 چندان قابل توجه نبوده است.

واژگان کلیدی: سختی، کامپوزیت رزین سایلوران، سفید کردن دندان

Introduction

Changing the resin matrix and production of composites with low polymerization shrinkage such as the silorane-based composite resins^[1] are one of the suggested strategies for reducing the stress generated by the process of polymerization shrinkage.

Prognosis and survival of restorations depend on the mechanical properties and biological characteristics of the used materials. Thus, chemical softening agents decrease hardness, clinical service and longevity of restorations.^[2] Microhardness is related to the mechanical properties of composite resins, their degradation and stainability. Bleaching treatments are usually done at the dental office or at home by using hydrogen peroxide derivatives.^[3] Due to the presence of an organic matrix, composite materials are more susceptible to chemical degradation compared to ceramic or metal restorations.^[4] Bleaching can slightly

change the enamel surface and negatively affect the surface quality of composite restorations in the mouth.^[5] Studies on the effects of bleaching on microhardness of restorative materials have reported controversial results^[6-11] and these effects are claimed to be material-dependent. Number of studies on the impact of bleaching on microhardness^[12-14] of silorane-based composites is limited. Considering the fact that changes in microhardness are related to the type of material, matrix and filler, a question still remains whether a locally made bleaching agent is capable of affecting the microhardness of recent silorane-based composite restorations. The present study sought to compare the effects of two bleaching agents on microhardness of 3 composites with different resin bases (silorane- and methacrylate-based), filler volume and filler type (nanofilled and microhybrid).

Methods

The materials used in this study are well described in table 1.

Specimen preparation

A total of 54 A3 shade composite discs (n=18 for each composite resin) measuring 2mm in thickness and 10mm in diameter were fabricated by using a stainless steel mold and light-cured using an LED light-curing unit (Valo, Ultradent) with 1000 mW/cm² intensity from each side of the mould for 20s. Then an operator polished the specimens with 1200, 1500, 2000, 2500 and 3000 grit silicon carbide abrasive papers. Polished specimens were placed in an ultrasonic bath containing distilled water for 3min for elimination of debris and then stored in distilled water for 24h to allow completion of polymerization.

Bleaching treatment

Each composite group was randomly divided into 3 subgroups (n=6). Subgroup 1 was stored in distilled water as the control group. The remaining two subgroups were subjected to bleaching with Kimia 16% carbamide peroxide (16%CP) 4h daily for 2 weeks and Kimia 35% carbamide peroxide (35%CP) only once for 40min, respectively. For bleaching

treatment, specimens were immersed in the bleaching gel for the respective time periods. After each time of treatment, specimens were rinsed and cleaned with a soft brush for 1 min. At the time intervals between treatments, specimens were stored in screw-top vials containing distilled water at room temperature and the distilled water was refreshed daily for all groups.

Microhardness testing

Microhardness of specimens was measured at baseline and after bleaching in the test groups and at baseline and after 2 weeks of storage in distilled water in control groups by using a digital microhardness tester (Vickers hardness testing machine) with a Vickers indenter at the load of 100 g and dwell time of 20 s at room temperature. Three indentations were made on each specimen with more than 1 mm distance from the disc margins and the mean of microhardness value was calculated by using the measurements done at the three indentation points. Vickers hardness was calculated by measuring the length of the two diagonals of the indentation and using the formula below^[15]: $VH=1.854F/d^2$

Where F is the applied force and d is the mean length of the two diagonals of the indentation

Table 1. Materials used in this study, their composition and manufacturer

Material	Type	Content	Manufacturer
Kimia Teeth Whitening System (home)	16% carbamide peroxide (gel)	Carbamide peroxide	Kimia, Chimie Dent, Iran
Kimia Teeth Whitening System (office)	35% carbamide peroxide (powder and liquid)	carbamide peroxide(liquid) Sio2(gelling powder)	Kimia, Chimie Dent, Iran
Filtek Z250	Microhybrid methacrylate-based composite	Bis-GMA, Bis-EMA, UDMA, TEGDMA Filler: Zirconia, silica (78% weight)(60% volume)(size 0.01-3.5 μ m)	3M ESPE, St. Paul, MN, USA
Filtek Z350 XT Enamel	Nanofilled methacrylate-based composite	Combination of aggregated zirconia/silica Cluster filler, Bis-GMA, UDMA, TEGDMA	3M ESPE, St. Paul, MN, USA
Filtek P90	Silorane-based composite (microhybrid)	Silorane resin, initiating system: comphorquinone, iodonium salt, Electron donor Quartz filler, Yttrium Fluoride (76% weight, 55% volume, size: 0.04-1.7 μ m) Stabilizers, pigments	3M ESPE, St. Paul, MN, USA

Statistical Analysis

Microhardness values were analyzed with repeated measures ANOVA. If the interaction effect between intervention and repeated factors was significant, the paired-t test was used for the comparison of the VH values before and after bleaching of each group, and two-way ANOVA was applied for between-group comparisons (before or after bleaching).

If the interaction effect between the type of composite and bleaching agent was significant, one-way ANOVA and if it was insignificant, the Tukey's HSD test was used. For multiple comparisons, Tukey's HSD test was also applied.

Results

Table 2 shows the microhardness values of the 3 under study composite resins in the control, home bleaching and office bleaching groups before and after the intervention (bleaching).

The type of composite resin ($p<0.001$) had a significant effect; whereas, the bleaching agent ($p=0.06$) and the interaction of bleaching agent and type of composite resin had no significant effect on microhardness values of specimens before the intervention ($p=0.209$). Before bleaching, microhardness values of FiltekZ250 (Z250) and Filtek Z350XT Enamel (Z350) were not significantly different ($p=0.293$) but significant differences were found between Z250 and FiltekP90 (P90) ($p<0.0001$) and P90 and Z350 ($p<0.0001$) in terms of microhardness value. Type of composite ($p<0.001$),

bleaching agent ($p<0.001$) and the interaction of type of composite and the bleaching agent ($p<0.001$) had significant effects on microhardness values of specimens after bleaching treatment.

Within each bleaching group, significant differences existed in microhardness values of composite resins ($p<0.001$ for all). No significant differences were observed in microhardness of Z250 and Z350 composites in the control, office and home bleaching subgroups ($p=0.47$, $p=0.19$ and $p=0.63$, respectively).

However, the difference in microhardness between Z250 and P90 ($p<0.001$ for all subgroups) and also Z350 and P90 ($p<0.001$ for all subgroups) was statistically significant.

Significant differences were observed in before- and after-bleaching microhardness values of Z250, Z350 and P90 ($p<0.001$, $p<0.001$ and $p=0.008$, respectively). Significant differences were shown in microhardness of Z250 specimens between the two subgroups of control and home bleaching ($p<0.001$) and control and office bleaching ($p<0.001$) after the intervention. However, the microhardness of office bleaching and home bleaching subgroups of Z250 after bleaching was not significantly different ($p=0.99$). Moreover, significant differences were detected in microhardness of Z350 specimens between the two subgroups of control and home bleaching ($p<0.001$) and control and office bleaching ($p<0.001$) in post-intervention. But, the microhardness of office bleaching and home bleaching subgroups of Z250 after bleaching was not significantly different ($p=0.94$).

Table2. The mean \pm SD of Vickers Hardness values for each composite resin and bleaching agent*

Composite Bleaching	Z250		Z350		P90	
	Before	After	Before	After	Before	After
16%CP	105.63 \pm 5.45	95.54 \pm 1.75	110.41 \pm 6.77	98.22 \pm 3.57	67.21 \pm 3.44	65.69 \pm 1.81
35%CP	115.97 \pm 5.95	94.39 \pm 6.31	108.68 \pm 4.89	96.57 \pm 2.71	70.91 \pm 1.56	68.17 \pm 1.26
Control	110.78 \pm 3.92	111.7 \pm 7.08	109.17 \pm 4.49	108.43 \pm 3.85	66.76 \pm 2.38	65.52 \pm 1.19

*Same superscript letter showed statistically no significant differences between groups.

($p<0.05$ was statistically considered significant).

Similarly in P90 group, microhardness values of control and office bleaching ($p=0.009$) and home and office bleaching ($p=0.02$) subgroups were significantly different after the intervention but no such difference was found in microhardness between the control and home bleaching subgroups ($p=0.99$).

Discussion

In the present study, baseline microhardness of P90 (silorane-based composite resin) was lower than that of methacrylate-based composite resins. Filtek P90 is filled with a combination of fine quartz and radiopaque yttrium fluoride particles and is classified as a microhybrid composite.

The filler content of this composite is 76% weight percent. Knoop hardness of quartz and zirconia particles was 820 and 1160, respectively^[1]. Zirconia particles were incorporated into the composition of the two methacrylate-based composites used in this study; which may be the reason for lower microhardness of P90.

Moreover, another study showed that silorane-based composites had relatively higher flexural strength, flexural modulus and fracture toughness but relatively lower compressive strength and hardness compared to methacrylate-based composite resins.^[16]

In this study, treatment with 16%CP and 35% CP significantly decreased the microhardness of Z250 and Z350 (compared to baseline) in comparison with the control group but no such effect was observed in P90 which was in agreement with Mourouzis et al.^[17]. Carbamide peroxide is a compound with hydrogen peroxide incorporated into its composition.

Carbamide peroxide is broken down into hydrogen peroxide and urea in a 1/3-2/3 ratio^[18]. Hydrogen peroxide is also broken down into perhydroxyl (HO_2^-) and O^- free radicals. Perhydroxyl is a very active free radical with potent oxidizing potential.

It affects macromolecules of the pigments and can lead to degradation of resin matrix and softening of composite resin.^[18] Moreover, free radicals can target

the resin-filler interface in composite resins^[4] causing microscopic cracks^[19] and compromising the surface hardness of composite resins.

Effect of bleaching agents on surface microhardness has been the subject of numerous investigations yielding controversial results. In some studies^[2,7,11] the use of higher concentrations of hydrogen peroxide has not caused significant changes in microhardness of composites; whereas, the other studies have shown that the surface microhardness of tooth-colored restorations is decreased following in-office bleaching^[20]; which is in agreement with our obtained results.

Atali and Topbasi^[12] reported changed microhardness of hybrid, nanohybrid, nano super-filled and silorane composites following bleaching treatments with 35% and 38% hydrogen peroxide. Nano-based composites were less affected than hybrid or silorane-based composites.

These findings were somehow in contrast to the results of present study. AlQahtani^[13] stated that 10% carbamide peroxide whitening agent had small effects on decreasing the microhardness of microhybrid composites. However, its effects on reducing the microhardness of nanofilled, silorane-based and hybrid composites were significant.

These results were different from our findings. Such differences may be attributed to the different methodology of studies, type and concentration of bleaching agents, type of composite or other factors. Difference in microhardness values after the same bleaching regimen may be attributed to the difference in organic matrix of polymers, filler content and size of particles. Filtek Z250 is a microhybrid composite with 78% weight percent filler and 0.01-3.5 μ size particles and Filtek Z350 is a nanofilled composite with a combination of 20nm silica nano-filters and 0.4-0.6 μ zirconia-silica nanoclusters.^[21]

Although some published studies have shown that this composite has mechanical properties similar to those of hybrid and midi-filled composites^[22-24], high surface/volume ratio due to the presence of silica

particles may increase its water sorption and cause destruction of polymer matrix-filler interface^[25-26] and lead to a possible drop in some mechanical properties.^[27]

There was a high possibility that in this study, bleaching agents decreased the microhardness of this composite by affecting the matrix-filler interface. One important characteristic of P90 is its superhydrophobicity due to the presence of siloxane in its chemical formulation causing its insolubility.^[28] This was probably responsible for no significant reduction in microhardness of this composite following the application of bleaching agents.

In current study, the effects of 4h daily application of 16% CP for 14 days and one time 40min application of 35% CP on microhardness of methacrylate-based composites were not significantly different. Some researchers discussed that increasing the concentration of bleaching gel increases the concentration of released H₂O₂ that may cause higher degradation of restorative materials.^[10, 29-30]

Some others reported that increasing the concentration of bleaching agents had no effect on microhardness of composite resins^[11, 14] which was in concord with our findings.

In addition, it indicated that the cumulative effect of low concentration of peroxide in chemical formulation of CP over time could cause degradation similar to that of a high-concentration agent with fewer applications in our two understudy methacrylate-based composites. Overall, the effects of these two bleaching agents were not similar on P90 which confirms the findings of Atali and Topbasi.^[12]

Conclusions

Beside the limitation of this study, silorane-based composite showed lower microhardness. But it did not decreased significantly after bleaching.

Acknowledgments

The authors express their thanks to Tehran University of Medical Sciences, International Campus for financial support of this research. They also appreciate the assistance of Kharazi Fard for statistical analysis.

Funding: This study was a part thesis and research project (Grant No: 91-03-168-20492) supported and funded by Tehran University of Medical Sciences, International Campus

Conflict of interest: We declare that there is no conflict of interest.

References

1. D'Alpino PH, Bechtold J, Santos PJ, Alonso RC, Di Hipolito V, Silikas N, et al. Methacrylate- and silorane-based composite restorations: Hardness, depth of cure and interfacial gap formation as a function of the energy dose. *Dent Mater* 2011;27:1162-9.
2. Yap AU, Wattanapayungkul P. Effects of in-office tooth whiteners on hardness of tooth-colored restoratives. *Oper Dent* 2002;27:137-41.
3. Summitt JB, Robbins JW. *Fundamentals of operative dentistry*. 3rd ed. Chicago: Quintessence Pub Co; 2006. p.429-31.
4. Hannig C, Duong S, Becker K, Brunner E, Kahler E, Attin T. Effect of bleaching on subsurface micro-hardness of composite and a polyacid modified composite. *Dent Mater* 2007;23:198-203.
5. Silva Costa SX, Becker AB, de Souza Rastelli AN, de Castro Monteiro Loffredo L, de Andrade MF, Bagnato VS. Effect of four bleaching regimens on color changes and microhardness of dental nanofilled composite. *Int J Dent* 2009; 313845.
6. Polydorou O, Hellwig E, Auschill TM. The effect of at-home bleaching on the microhardness of six esthetic restorative materials. *J Am Dent Assoc* 2007;138:978-84.

7. Polydorou O, Monting JS, Hellwig E, Auschill TM. Effect of in-office tooth bleaching on the microhardness of six dental esthetic restorative materials. *Dent Mater* 2007;23:153-8.
8. Bayindir F, Colak K, Uzun I. Effect of tooth whitener on microhardness of tooth colour restorative materials. *Mater Res Innov* 2009;13:28-31.
9. Lee JH, Kim HI, Kim KH, Kwon YH. Effect of bleaching agents on the fluoride release and microhardness of dental materials. *J Biomed Mater Res* 2002;63:535-41.
10. Jung CB, Kim HI, Kim KH, Kwon YH. Influence of 30% hydrogen peroxide bleaching on compomers in their surface modifications and thermal expansion. *Dent mater J* 2002;21:396-403.
11. Garcia-Godoy F, Garcia-Godoy A. Effect of bleaching gels on the surface roughness, hardness, and micromorphology of composites. *Gen Dent* 2002;50:247-50.
12. Atali PY, Topbaş FB. The effect of different bleaching methods on the surface roughness and hardness of resin composites. *J Dent Oral Hyg* 2011;3:10-7.
13. AlQahtani M. The Effect of a 10% Carbamide Peroxide Bleaching Agent on the Microhardness of Four Types of Direct Resin-Based Restorative Materials. *Oper Dent* 2013;38:316-23.
14. Hashemikamangar SS, Kiakooori K, Mirzaii M, Fard MJK. Effects of 15% Carbamide Peroxide and 40% Hydrogen Peroxide on the Microhardness and Color Change of Composite Resins. *J Dent Teh Uni Med Sci* 2014;11:196-209.
15. Mujdeci A, Gokay O. Effect of bleaching agents on the microhardness of tooth-colored restorative materials. *J Prosthet Dent* 2006;95:286-9.
16. Lien W, Vandewalle KS. Physical properties of a new silorane-based restorative system. *Dent Mater* 2010;26:337-44.
17. Mourouzis P, Koulaouzidou EA, Helvatjoglou Antoniades M. Effect of in-office bleaching agents on physical properties of dental composite resins. *Quintessence Int* 2013;44:295-302.
18. Fasanaro TS. Bleaching teeth: history, chemicals, and methods used for common tooth discolorations. *J Evid Based Dent Pract* 1992;4:71-8.
19. Attin T, Hannig C, Wiegand A, Attin R. Effect of bleaching on restorative materials and restorations--a systematic review. *Dent Mater* 2004;20:852-61.
20. Taher NM. The effect of bleaching agents on the surface hardness of tooth colored restorative materials. *J Contemp Dent Pract* 2005;6:18-26.
21. Mitra SB, Wu D, Holmes BN. An application of nanotechnology in advanced dental materials. *JADA* 2003;134:1382.
22. Beun S, Glorieux T, Devaux J, Vreven J, Leloup G. Characterization of nanofilled compared to universal and microfilled composites. *Dent Mater* 2007;23:51-9.
23. Rodrigues Junior SA, Zanchi CH, Carvalho RV, Demarco FF. Flexural strength and modulus of elasticity of different types of resin-based composites. *Braz Oral Res* 2007;21:16-21.
24. Hatanaka GR, Abi-Rached Fde O, Almeida-Junior AA, Cruz CA. Effect of carbamide peroxide bleaching gel on composite resin flexural strength and microhardness. *Braz Dent J* 2013;24:263-6.
25. da Silva EM, Goncalves L, Guimaraes JG, Poskus LT, Fellows CE. The diffusion kinetics of a nanofilled and a midfilled resin composite immersed in distilled water, artificial saliva, and lactic acid. *Clin Oral Investig* 2011;15:393-401.
26. Kalachandra S, Wilson T. Water sorption and mechanical properties of light-cured proprietary composite tooth restorative materials. *Biomaterials* 1992;13:105-9.
27. Curtis A, Shortall A, Marquis P, Palin W. Water uptake and strength characteristics of a nanofilled resin-based composite. *J Dent* 2008;36:186-93.

28. Eick JD, Smith RE, Pinzino CS, Kostoryz EL. Stability of silorane dental monomers in aqueous systems. *J Dent* 2006;34:405-10.
29. Minoux M, Serfaty R. Vital tooth bleaching: biologic adverse effects-a review. *Quintessence Int* 2008;39:645-59.
30. Campos I, Briso AL, Pimenta LA, Ambrosano G. Effects of bleaching with carbamide peroxide gels on microhardness of restoration materials. *J Esthet Restor Dent* 2003;15:175-82.